

Special Body, individually wrapped

35 % Chamotte 0 - 1,5 mm

Ceramic datas:

Dry shrinkage in %:

6-7

Firing temperature:

1070 °C

1140 °C

1240 °C

firing colour:

light red

dark red

red - brown

Firing shrinkage in %:

4

5,6

6

Water absorption in %:

13

9

8

