

Plastic body No. 208, individually wrapped

Chemical analysis:

SiO ₂	75.0 %
Al ₂ O ₃	19.8 %
TiO ₂	1.4 %
Fe ₂ O ₃	0.9 %
CaO	0.2 %
MgO	0.3 %
K ₂ O	2.2 %
Na ₂ O	0.1 %

Ceramic data:

Dry shrinkage in %:

6

Firing temperature:

1070 °C

1140 °C

1240 °C

Firing colour:

white

light-cream

cream

Firing shrinkage in %:

2

4

7

Water absorption in %:

10

7

1

**Coefficient of thermal
expansion (CTE):**

20 °C - 400 °C

66

20 °C - 500 °C

69

20 °C - 600 °C

83

CTE * 10⁻⁷/K